

Heatbath/Park Cartecsal Neutral Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

Mixture specified and developed for the U.S. Department of Energy for processing alloys containing uranium where chloride compounds are objectionable and where cleaning is important. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-Cartecsal-Neutral-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	432 Â°C	810 Â°F	
Maximum Service Temperature, Air	954 Â°C	1750 Â°F	Upper limit of working range
Minimum Service Temperature, Air	454 Â°C	850 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China