

Heatbath/Park High Speed 75 Neutral Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

Used in forging, brazing and high temperature hardening of high speed, high carbon, high chrome steels and stainless steels. Finish ground tools can be heated in High Speed 75 without harming critical areas such as threaded sections. Formulated per MIL-S-10699-B, Class 7A
Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-High-Speed-75-Neutral-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	954 Â°C	1750 Â°F	
Maximum Service Temperature, Air	1320 Â°C	2400 Â°F	Upper limit of working range
Minimum Service Temperature, Air	1040 Â°C	1900 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China