

Heatbath/Park High Temp Draw Salt Quenching and Tempering Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

Salt mixture particularly suitable for ausquenching/austempering. (430 Parkettes) Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-High-Temp-Draw-Salt-Quenching-and-Tempering-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	221 Â°C	430 Â°F	
Maximum Service Temperature, Air	593 Â°C	1100 Â°F	Upper limit of working range
Minimum Service Temperature, Air	249 Â°C	480 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China