

Heatbath/Park Marquench Oil M

Category : Fluid , Quenchant

Material Notes:

An accelerated quench oil designed for applications at 250Â° to 350Â°F. The use of this "hot" oil is commonly encountered in carburizing and carbonitriding furnaces or where parts are prone to distortion and cracking. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-Marquench-Oil-M.php

Physical Properties	Metric	English	Comments
Saybolt Viscosity at 100Â°F	350 SUS	350 SUS	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 Â°C	350 Â°F	Upper limit of working range
Minimum Service Temperature, Air	121 Â°C	250 Â°F	Lower limit of working range
Flash Point	224 Â°C	435 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China