

Heatbath/Park No-Carb Stop-Off/Protective Coating for Steel

Category: Ceramic, Fluid, Other Engineering Material, Ceramic/Metallic Coating

Material Notes:

Water-base paint containing copper used to prevent carburization or decarburization of steel during heating for hardening, carburizing, annealing, normalizing, forging or rollingInformation provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-No-Carb-Stop-OffProtective-Coating-for-Steel.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	927 °C	1700 °F	Upper limit of working range
Minimum Service Temperature, Air	760 °C	1400 °F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China