

Heatbath/Park Polyquench 15 Water-Based Quenchant

Category : Fluid , Quenchant

Material Notes:

Water solution of organic polymer, corrosion inhibitors, biocide and anti-foaming agents. The polymer has normal solubility and greater washability than other synthetic quenchant. Typical concentration is 15%. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-Polyquench-15-Water-Based-Quenchant.php

Physical Properties	Metric	English	Comments
Saybolt Viscosity at 100°F	3.3 SUS	3.3 SUS	At 100°F in SUS; cSt

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	65.6 °C	150 °F	Upper limit of working range
Minimum Service Temperature, Air	26.7 °C	80.0 °F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China