

## Heatbath/Park Polyquench 20 Water-Based Quenchant

Category : Fluid , Quenchant

### Material Notes:

Water solution of standard, "Type I", polyalkylene glycol quenchant. The polymer is inversely soluble above 1650°F. Typical concentration is 15%. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HeatbathPark-Polyquench-20-Water-Based-Quenchant.php](http://www.lookpolymers.com/polymer_HeatbathPark-Polyquench-20-Water-Based-Quenchant.php)

Physical Properties	Metric	English	Comments
Saybolt Viscosity at 100°F	3.9 SUS	3.9 SUS	At 100°F in SUS; cSt

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	65.6 °C	150 °F	Upper limit of working range
Minimum Service Temperature, Air	26.7 °C	80.0 °F	Lower limit of working range

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China