

Heatbath/Park Sta-Hard 45 High Speed Hardening Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

A stable salt for neutral heating of ferrous and nonferrous alloys. Sta-Hard45 is similar to Sta-Hard 17, but provides higher working temperatures. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-Sta-Hard-45-High-Speed-Hardening-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	788 Â°C	1450 Â°F	
Maximum Service Temperature, Air	1150 Â°C	2100 Â°F	Upper limit of working range
Minimum Service Temperature, Air	843 Â°C	1550 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China