

## Heatbath/Park Tempering C-ALHT for Aluminum Solution Heat Treating

Category : Ceramic , Fluid , Quenchant

### Material Notes:

A granular mixture of sodium and potassium nitrates formulated per MIL-S-10699-B, class 11 and MIL-H-6088. The salt is colored pink for identification purposes. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HeatbathPark-Tempering-C-ALHT-for-Aluminum-Solution-Heat-Treating.php](http://www.lookpolymers.com/polymer_HeatbathPark-Tempering-C-ALHT-for-Aluminum-Solution-Heat-Treating.php)

Thermal Properties	Metric	English	Comments
Melting Point	221 Â°C	430 Â°F	
Maximum Service Temperature, Air	593 Â°C	1100 Â°F	Upper limit of working range
Minimum Service Temperature, Air	249 Â°C	480 Â°F	Lower limit of working range

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China