

Heatbath/Park Uni-Hard IR Neutral Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

Frequently used as a preheat for tool hardening or as a heating medium for continuous production hardening. Dragout is minimal because of high fluidity. Uni-Hard IR is water-soluble and non-hygroscopic. Nonferrous and precious metals as well as ferrous alloys can be treated in Uni-Hard IR. Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-Uni-Hard-IR-Neutral-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	549 Â°C	1020 Â°F	
Maximum Service Temperature, Air	927 Â°C	1700 Â°F	Upper limit of working range
Minimum Service Temperature, Air	593 Â°C	1100 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China