

## Henkel Hysol EA 9150 Composite Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

**Material Notes:**

Low viscosity, toughened system formulated for resin transfer molding. 250Å°F / 121Å°C cure and service temperature. Application:  
Composite Binding

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Henkel-Hysol-EA-9150-Composite-Resin.php](http://www.lookpolymers.com/polymer_Henkel-Hysol-EA-9150-Composite-Resin.php)

Physical Properties	Metric	English	Comments
Storage Temperature	25.0 Å°C	77.0 Å°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength	75.9 MPa	11000 psi	
Elongation at Break	5.0 %	5.0 %	
Tensile Modulus	2.85 GPa	413 ksi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	121 Å°C	250 Å°F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min @Temperature 121 Å°C	1.00 hour @Temperature 250 Å°F	
Pot Life	480 min	480 min	

Descriptive Properties	Value	Comments
Consistency	Low Viscosity	
Form	2 part	
Mix Ratio, Part A:Part B	100:88	
Peel Strength	Low	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China