

Henkel Hysol EA 9896 WPP Peel Ply

Category: Polymer, Film, Thermoplastic, Nylon

Material Notes:

Pre-impregnated, nylon peel ply product supplied in film form. Specially designed resin system capable of curing at $250 \hat{A}^{\circ} F / 121 \hat{A}^{\circ} C$. Compatible with state-of-the-art composite prepreg resin systems. Provides minimal residual peel ply fibers at the bond surface after curing and removal. Applications: Composite Surfacing Composite Bonding

Order this product through the following link:

http://www.lookpolymers.com/polymer_Henkel-Hysol-EA-9896-WPP-Peel-Ply.php

Physical Properties	Metric	English	Comments
Storage Temperature	-18.0 °C	-0.400 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	93.0 °C	199 °F	
Glass Transition Temp, Tg	93.0 °C	199 °F	wet
	132 °C	270 °F	dry

Processing Properties	Metric	English	Comments
Cure Time	90.0 - 120 min	1.50 - 2.00 hour	
	@Temperature 121 °C	@Temperature 250 °F	

Descriptive Properties	Value	Comments
Out-Time (days)	14	at 23°C

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China