

Heraeus Cleviosâ, ¢ P Conductive Sulfonate Polymer for Antistatic Coatings

Category: Polymer

Material Notes:

Poly(3,4-ethylenedioxythiophene)poly(styrenesulfonate), provided as an aqueous dispersion used to produce thin film antistatic coatings. Cleviosâ,¢ P is an antistatic material based on PEDOT:PSS – chemistry for electronics applications. This conductive polymer possesses high transmission in the visible spectrum transparent colorless to light blue coatings, good resistance to hydrolysis, and good thermal stability. Typical applications include the antistatic coating of PET or Polycarbonate films for antistatic trays and blister tapes, films for dust protection of components in the LCD industry, antistatic coating of glass, high quality antistatic-coated papers, and other ESD and dissipative applicationsApplication Methods: Dipping, Spraying, Printing (including gravure, slot-die)Information provided by Heraeus, Conductive Polymers Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Heraeus-Clevios-P-Conductive-Sulfonate-Polymer-for-Antistatic-Coatings.php

| Physical Properties | Metric | English | Comments |
|---------------------|-------------|-------------|-------------|
| Solids Content | 1.2 - 1.4 % | 1.2 - 1.4 % | As Supplied |
| рН | 1.5 - 2.5 | 1.5 - 2.5 | As Supplied |
| Viscosity | 60 - 100 cP | 60 - 100 cP | As Supplied |

| Optical Properties | Metric | English | Comments |
|-----------------------|---------------------------|-----------------------------|-----------------|
| | >= 85 % | >= 85 % | |
| Transmission, Visible | @Thickness 0.000100 mm | @Thickness 0.00000394 in | Applied Coating |

| Electrical Properties | Metric | English | Comments |
|--------------------------------|-----------------------|-----------------------|--|
| Electrical Resistivity | 0.0100 - 0.100 ohm-cm | 0.0100 - 0.100 ohm-cm | Applied Coating; formulated with DMSO or MEG |
| Surface Resistivity per Square | 1e+05 | 1e+05 | Applied Coating |

| Processing Properties | Metric | English | Comments |
|-----------------------|-------------------------|----------------------|--------------------------------|
| Shelf Life | 9.00 Month | 9.00 Month | |
| | @Temperature 20.0 °C | @Temperature 68.0 °F | in unopened original container |

| Descriptive Properties | Value | Comments |
|------------------------|--------|----------|
| Form Supplied | Liquid | |
| Odor | None | |



Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China