

Heraeus Cleviosâ, ¢ P Jet HC V2 Conductive Sulfonate Polymer for Antistatic **Coatings**

Category: Polymer

Material Notes:

Poly(3,4-ethylenedioxythiophene)poly(styrenesulfonate), provided as an aqueous dispersion used to produce thin film antistatic coatings. Cleviosâ,¢ P Jet HC V2 is an antistatic material based on PEDOT:PSS â€" chemistry for electronics applications. This conductive polymer is an inkjet formulation, acidic, high conductive version of Cleviosâ, ¢ P. Typical applications include the antistatic coating of PET or Polycarbonate films for antistatic trays and blister tapes, films for dust protection of components in the LCD industry, antistatic coating of glass, high quality antistatic-coated papers, and other ESD and dissipative applicationsInformation provided by Heraeus, Conductive **Polymers Division.**

Order this product through the following link:

http://www.lookpolymers.com/polymer_Heraeus-Clevios-P-Jet-HC-V2-Conductive-Sulfonate-Polymer-for-Antistatic-Coatings.php

| Physical Properties | Metric | English | Comments | |
|---------------------|----------------------|----------------------|-------------|--|
| Solids Content | 0.60 - 1.2 % | 0.60 - 1.2 % | As Supplied | |
| Viscosity | 5.0 - 20 cP | 5.0 - 20 cP | As Supplied | |
| | @Shear Rate 11.7 1/s | @Shear Rate 11.7 1/s | АЅ Зиррпеи | |

| Electrical Properties | Metric | English | Comments |
|------------------------|----------------|----------------|----------|
| Electrical Resistivity | 0.00330 ohm-cm | 0.00330 ohm-cm | |

| Processing Properties | Metric | English | Comments |
|-----------------------|-----------------------------|--------------------------------|--------------------------------|
| Shelf Life | 6.00 Month | 6.00 Month | in unopened original container |
| | @Temperature 5.00 - 30.0 °C | @Temperature 41.0 - 86.0 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|-------------|----------|
| Form Supplied | Blue Liquid | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Address: United North Road 215, Fengxian District, Shanghai City, China

Skype: lookpolymers