

Hexcel® HexPly® 954-2A Curing Cyanate Resin, G40-800 Fiber

Category : Polymer , Thermoset , Epoxy

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-954-2A-Curing-Cyanate-Resin-G40-800-Fiber.php

| Mechanical Properties | Metric | English | Comments |
|----------------------------|----------------------------------|------------------------------------|----------|
| Tensile Strength, Yield | 3017 MPa @Temperature 23.0 °C | 437600 psi @Temperature 73.4 °F | 0° |
| Tensile Modulus | 159 GPa @Temperature 23.0 °C | 23100 ksi @Temperature 73.4 °F | 0° |
| Compressive Yield Strength | 1510 MPa @Temperature 23.0 °C | 219000 psi @Temperature 73.4 °F | |
| Compressive Modulus | 158 GPa @Temperature 23.0 °C | 22900 ksi @Temperature 73.4 °F | |
| Shear Strength | 111 MPa @Temperature 22.0 °C | 16100 psi @Temperature 71.6 °F | 0° |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China