

Hexcel® HexPly® 954-3 Curing Cyanate Resin, M60J Fiber

Category : Polymer , Thermoset , Epoxy

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-954-3-Curing-Cyanate-Resin-M60J-Fiber.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	2151 MPa @Temperature 23.0 °C	312000 psi @Temperature 73.4 °F	0°
Tensile Modulus	365 GPa @Temperature 23.0 °C	52900 ksi @Temperature 73.4 °F	0°
Compressive Yield Strength	924 MPa @Temperature 23.0 °C	134000 psi @Temperature 73.4 °F	
Compressive Modulus	343 GPa @Temperature 23.0 °C	49700 ksi @Temperature 73.4 °F	
Shear Strength	78.0 MPa @Temperature 22.0 °C	11300 psi @Temperature 71.6 °F	0°

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China