

## Hexcel® HexPly® EH 84 120°C Curing Epoxy Matrix, High Strength 12k carbon UD tape Not Supported 150 g/m2

Category : Polymer , Thermoset , Carbon Fiber/Thermoset Composite , Epoxy , Epoxy/Carbon Fiber Composite

**Material Notes:**

Information provided by HexCel

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexcel-HexPly-EH-84-120C-Curing-Epoxy-Matrix-High-Strength-12k-carbon-UD-tape-Not-Supported-150-gm2.php](http://www.lookpolymers.com/polymer_Hexcel-HexPly-EH-84-120C-Curing-Epoxy-Matrix-High-Strength-12k-carbon-UD-tape-Not-Supported-150-gm2.php)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	2000 MPa	290000 psi	0°
Tensile Modulus	130 GPa	18900 ksi	0°
Flexural Yield Strength	2000 MPa	290000 psi	0°
Flexural Modulus	120 GPa	17400 ksi	0°
Compressive Yield Strength	1200 MPa	174000 psi	0°
Shear Strength	85.0 MPa	12300 psi	0° , Short Beam

Processing Properties	Metric	English	Comments
Shelf Life	14.0 Month	14.0 Month	
	@Temperature -18.0 °C	@Temperature -0.400 °F	

Descriptive Properties	Value	Comments
Fiber Volume (%)	60	
Tack Life (days)	30	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China