

Hexcel® HexPly® M34 75°C (167°F) Curing Epoxy Matrix, E-glass Balanced Fabric 300 g/m²

Category : Polymer , Thermoset , Epoxy , Epoxy/Glass SMC

Material Notes:

Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexPly-M34-75C-167F-Curing-Epoxy-Matrix-E-glass-Balanced-Fabric-300-gm2.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	600 MPa	87000 psi	0°
Tensile Modulus	21.0 GPa	3050 ksi	0°
Flexural Yield Strength	700 MPa	102000 psi	0°
Flexural Modulus	20.0 GPa	2900 ksi	0°
Compressive Yield Strength	540 MPa	78300 psi	0°
Shear Strength	50.0 MPa	7250 psi	0°, Short Beam

Processing Properties	Metric	English	Comments
Shelf Life	12.0 Month	12.0 Month	
	@Temperature -18.0 °C	@Temperature -0.400 °F	

Descriptive Properties	Value	Comments
Fiber Volume (%)	55	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China