

Hexcel® HexWeb® CFC™ -20-1/8-6.0 Composite Flooring Honeycomb Core

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Aramid

Material Notes:

Hexweb® CFC™ -20 is manufactured from NOMEX aramid fiber sheets. A thermosetting adhesive is used to bond these sheets at the nodes and, after expanding to the hexagonal configuration, the block is dipped in phenolic resin. After curing the resin, slices are cut to the desired thickness. Features: Specifically designed for aircraft flooring applications; Superior properties and performance over balsa and foam core materials; Proven durability in extensive flooring tests; Significant weight advantage over balsa and foam core materials; Exceeds all FAA safety requirements; Excellent property retention at 350°F; Moisture and fungus resistant. Applications: Hexweb® CFC™ -20 honeycomb core was specifically developed to provide a tough, lightweight core material for use in aircraft flooring systems. A range of product densities are available to fit a wide variety of loading requirements. The core material when bonded to metallic or nonmetallic facings provides a flooring panel sheet which may be cut or contoured to fit any aircraft flooring module.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-CFC-20-18-60-Composite-Flooring-Honeycomb-Core.php

Physical Properties	Metric	English	Comments
Density	0.0961 g/cc	0.00347 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 5.00 MPa	>= 725 psi	Bare, min, preliminary value obtained from limited testing
	>= 5.38 MPa	>= 780 psi	Stabilized, min, preliminary value obtained from limited testing
	6.65 MPa	965 psi	Bare, typ, preliminary value obtained from limited testing
	7.17 MPa	1040 psi	Stabilized, typ, preliminary value obtained from limited testing
Shear Modulus	0.0552 GPa	8.00 ksi	Plate Shear, W Direction, typ, preliminary value obtained from limited testing
	0.0931 GPa	13.5 ksi	Plate Shear, L Direction, typ, preliminary value obtained from limited testing
Shear Strength	>= 1.24 MPa	>= 180 psi	Plate Shear, W Direction, min, preliminary value obtained from limited testing
	1.65 MPa	240 psi	Plate Shear, W Direction, typ, preliminary value obtained from limited testing
	>= 2.00 MPa	>= 290 psi	Plate Shear, L Direction, min, preliminary value obtained from limited testing
			Plate Shear, L Direction, typ,

Mechanical Properties	2.69 MPa Metric	390 psi English	preliminary value obtained from initial testing
-----------------------	--------------------	--------------------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China