

**Hexcel® HexWeb® HRH-10 - 1/8- 3.0 Aramid Fiber/Phenolic Resin Honeycomb**

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Aramid , Phenolic

**Material Notes:**

Designation: Material-Cell Size-Density.Hexweb® HRH-10 is manufactured from NOMEX® aramid fiber sheets. A thermosetting adhesive is used to bond these sheets at the nodes, and after expanding to the hexagonal or OX-Core® configuration, the block is dipped in phenolic resin. After curing the resin, slices are cut to the desired thickness. For special applications, such as air directionalizing, HexWeb® HRH-10 can be provided without the phenolic resin. Using this process, a wide range of cell sizes, paper thicknesses, and densities can be produced.Information provided by HexCel

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexcel-HexWeb-HRH-10-18-30-Aramid-FiberPhenolic-Resin-Honeycomb.php](http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRH-10-18-30-Aramid-FiberPhenolic-Resin-Honeycomb.php)

Physical Properties	Metric	English	Comments
Density	0.0481 g/cc	0.00174 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 1.62 MPa	>= 235 psi	Bare, min
	>= 1.86 MPa	>= 270 psi	Stabilized, min
	2.07 MPa	300 psi	Bare, typ
	2.24 MPa	325 psi	Stabilized, typ
Compressive Modulus	0.138 GPa	20.0 ksi	Stabilized, typ
Shear Modulus	0.0241 GPa	3.50 ksi	Plate Shear, W Direction, typ
	0.0414 GPa	6.00 ksi	Plate Shear, L Direction, typ
Shear Strength	>= 0.586 MPa	>= 85.0 psi	Plate Shear, W Direction, min
	0.689 MPa	100 psi	Plate Shear, W Direction, typ
	>= 1.07 MPa	>= 155 psi	Plate Shear, L Direction, min
	1.21 MPa	175 psi	Plate Shear, L Direction, typ

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China