

Hexcel® HexWeb® HRH-10 - 3/16 - 4.0 Aramid Fiber/Phenolic Resin Honeycomb

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Aramid , Phenolic

Material Notes:

Designation: Material-Cell Size-Density.Hexweb® HRH-10 is manufactured from NOMEX® aramid fiber sheets. A thermosetting adhesive is used to bond these sheets at the nodes, and after expanding to the hexagonal or OX-Core® configuration, the block is dipped in phenolic resin. After curing the resin, slices are cut to the desired thickness. For special applications, such as air directionalizing, HexWeb® HRH-10 can be provided without the phenolic resin. Using this process, a wide range of cell sizes, paper thicknesses, and densities can be produced.Information provided by HexCel

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRH-10-316-40-Aramid-FiberPhenolic-Resin-Honeycomb.php

Physical Properties	Metric	English	Comments
Density	0.0641 g/cc	0.00231 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 2.96 MPa	>= 430 psi	Bare, min
	>= 3.24 MPa	>= 470 psi	Stabilized, min
	3.45 MPa	500 psi	Bare, typ
	3.72 MPa	540 psi	Stabilized, typ
Compressive Modulus	0.193 GPa	28.0 ksi	Stabilized, typ
Shear Modulus	0.0324 GPa	4.70 ksi	Plate Shear, W Direction, typ
	0.0538 GPa	7.80 ksi	Plate Shear, L Direction, typ
Shear Strength	>= 0.758 MPa	>= 110 psi	Plate Shear, W Direction, min
	0.965 MPa	140 psi	Plate Shear, W Direction, typ
	>= 1.48 MPa	>= 215 psi	Plate Shear, L Direction, min
	1.69 MPa	245 psi	Plate Shear, L Direction, typ

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China