

Hexcel® HexWeb® HRH-327 - 1/8 - 3.2 Fiberglass Reinforced Polyimide Honeycomb

Category : Other Engineering Material , Composite Fibers , Polymer , Thermoset , Polyimide, TS

Material Notes:

Designation: Material-Cell Size (inches)-DensityHexWeb® HRH-327 is a glass-fabric, bias weave reinforced plastic honeycomb that incorporates a polyimide resin system for the node adhesive as well as both the initial and final web impregnations. This material has been developed for extended service temperatures up to 500°F with short-term capabilities up to 700°F. Unless other specified, material will have standard postcure.**Features:** High-strength retention up to 500°F continuous service; 700°F short and intermittent term exposures; All polyimide resin and adhesive system; Good dielectric properties; Good insulative properties; Compatible with Hexcel polyimide adhesive, foam, and prepreg.**Applications:** A high-temperature nonmetallic honeycomb for use in sandwich structures that require good electrical properties or that see service temperatures in the range of 350°F-500°F. Applications include sandwich structures for Mach 2 and Mach 3 aircraft, high-energy radomes, structural and acoustical engine inlets and liners.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRH-327-18-32-Fiberglass-Reinforced-Polyimide-Honeycomb.php

Physical Properties	Metric	English	Comments
Density	0.0513 g/cc	0.00185 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 1.52 MPa	>= 220 psi	Stabilized, min
	2.14 MPa	310 psi	Stabilized, typ
Compressive Modulus	0.186 GPa	27.0 ksi	Stabilized, typ
Shear Modulus	0.0517 GPa	7.50 ksi	Plate Shear, W Direction, typ
	0.131 GPa	19.0 ksi	Plate Shear, L Direction, typ
Shear Strength	>= 0.483 MPa	>= 70.0 psi	Plate Shear, W Direction, min
	0.655 MPa	95.0 psi	Plate Shear, W Direction, typ
	>= 0.965 MPa	>= 140 psi	Plate Shear, L Direction, min
	1.34 MPa	195 psi	Plate Shear, L Direction, typ

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	260 °C	500 °F	Extended
	371 °C	700 °F	Short Term

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China