

Hexcel® HexWeb® HRH-36® Flex-Core® HRH-36 - F50 - 2.0 Aramid Honeycomb

Category : Polymer , Thermoset , Aramid , Phenolic

Material Notes:

Designation: Material-Cell Size (cells per lineal foot in W direction)-Density (lb per cubic foot)HexWeb® HRH-36® Flex-Core® aramid paper is reinforced with a high temperature phenolic resin. This product provides good retention of strength for temperatures up to 350°F.Features: Specifically designed for formability; Retains mechanical properties in the curved condition; Offers cost savings for curved panels.Applications: The HexWeb® HRH-36® Flex-Core® cell configuration, as opposed to the standard hexagonal cell honeycomb, provides for exceptional formability into compound curvatures with reduced anticlastic curvature and controlled buckling of the cell walls. When formed into tight radii, HexWeb® Flex-Core® provides higher shear strengths than comparable hexagonal cores of equivalent density. HexWeb® Flex-Core® applications exist wherever extreme curvature dictates a flexible cell geometry, e.g. radomes, ducts, leading edges of wings and stabilizers. HexWeb® HRH-36® Flex-Core® offers a weight reduction over higher density NOMEX® cores.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRH-36-Flex-Core-HRH-36-F50-20-Aramid-Honeycomb.php

Physical Properties	Metric	English	Comments
Density	0.0320 g/cc	0.00116 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	1.34 MPa	195 psi	Stabilized, typical value
Shear Modulus	0.0310 GPa	4.50 ksi	Plate Shear, W Direction, typical value
	0.0655 GPa	9.50 ksi	Plate Shear, L Direction, typical value
Shear Strength	0.386 MPa	56.0 psi	Plate Shear, W Direction, typical value
	0.703 MPa	102 psi	Plate Shear, L Direction, typical value

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China