

Hexcel® HexWeb® HRH-36® Flex-Core® HRH-36 - F50 - 2.5 Aramid Honeycomb

Category : Polymer , Thermoset , Aramid , Phenolic

Material Notes:

Designation: Material-Cell Size (cells per lineal foot in W direction)-Density (lb per cubic foot)HexWeb® HRH-36® Flex-Core® aramid paper is reinforced with a high temperature phenolic resin. This product provides good retention of strength for temperatures up to 350°F.Features: Specifically designed for formability; Retains mechanical properties in the curved condition; Offers cost savings for curved panels.Applications: The HexWeb® HRH-36® Flex-Core® cell configuration, as opposed to the standard hexagonal cell honeycomb, provides for exceptional formability into compound curvatures with reduced anticlastic curvature and controlled buckling of the cell walls. When formed into tight radii, HexWeb® Flex-Core® provides higher shear strengths than comparable hexagonal cores of equivalent density. HexWeb® Flex-Core® applications exist wherever extreme curvature dictates a flexible cell geometry, e.g. radomes, ducts, leading edges of wings and stabilizers. HexWeb® HRH-36® Flex-Core® offers a weight reduction over higher density NOMEX® cores.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRH-36-Flex-Core-HRH-36-F50-25-Aramid-Honeycomb.php

Physical Properties	Metric	English	Comments
Density	0.0400 g/cc	0.00145 lb/in ³	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	1.59 MPa	230 psi	Stabilized, typical value
Shear Modulus	0.0324 GPa	4.70 ksi	Plate Shear, W Direction, typical value
	0.0669 GPa	9.70 ksi	Plate Shear, L Direction, typical value
Shear Strength	0.469 MPa	68.0 psi	Plate Shear, W Direction, typical value
	0.883 MPa	128 psi	Plate Shear, L Direction, typical value

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China