

## Hexcel® HexWeb® HRP - 1/4 - 5.0 Fiberglass/Phenolic Honeycomb

**Category :** Ceramic , Glass , Glass Fiber , Other Engineering Material , Composite Core Material , Composite Fibers , Polymer , Thermoset , Phenolic

### Material Notes:

**Designation:** Material-Cell Size (inches)-DensityHexWeb® HRP is a glass fabric reinforced honeycomb in which a heat-resistant phenolic resin is used both for initial and final impregnations. This product was developed for use at service temperatures up to 350°F. However, it is also well suited for short exposures at high temperatures. The HexWeb® HRP-series honeycomb is available in the standard hexagonal configuration, as well as in the two formale geometries - OX-Core® and Flex-Core®. **Features:** High strength up to 350°F; Good insulation and dielectric properties; Good bonding surface; Readily heat formed. **Applications:** HexWeb® HRP has proven to be an excellent core material for radomes, aircraft structural parts and fairings, heat shields, and other assemblies that see elevated temperature service.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexcel-HexWeb-HRP-14-50-FiberglassPhenolic-Honeycomb.php](http://www.lookpolymers.com/polymer_Hexcel-HexWeb-HRP-14-50-FiberglassPhenolic-Honeycomb.php)

Physical Properties	Metric	English	Comments
Density	0.0801 g/cc	0.00289 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Compressive Yield Strength	>= 3.65 MPa	>= 530 psi	Bare, min
	>= 4.55 MPa	>= 660 psi	Stabilized, min
	4.69 MPa	680 psi	Bare, typ
	5.65 MPa	820 psi	Stabilized, typ
Compressive Modulus	0.579 GPa	84.0 ksi	Stabilized, typ
Shear Modulus	0.0689 GPa	10.0 ksi	Plate Shear, W Direction, typ
	0.138 GPa	20.0 ksi	Plate Shear, L Direction, typ
Shear Strength	>= 1.24 MPa	>= 180 psi	Plate Shear, W Direction, min
	1.59 MPa	230 psi	Plate Shear, W Direction, typ
	>= 2.10 MPa	>= 305 psi	Plate Shear, L Direction, min
	2.76 MPa	400 psi	Plate Shear, L Direction, typ

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	350 °F	High strength retained

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China