## Hexcel® HexWeb® HRP/F50 - 3.5 Nonmetallic Flex-Core Honeycomb

Category : Ceramic , Glass , Glass Fiber , Other Engineering Material , Composite Fibers , Polymer , Thermoset , Phenolic

## Material Notes:

Designation: Material/Cell Size (cells per lineal foot in W direction)-DensityHexcel manufactures two types of nonmetallic reinforced plastic HexWeb® Flex-Core®: HexWeb® HRP - Fiberglasses cloth reinforced with a high temperature phenolic resin. This product provides good retention of strength for temperatures up to 350°F.HexWeb® HRH-10 - NOMEX® aramid paper reinforced with a high temperature phenolic resin. This product provides good retention of strength for temperatures up to 300°F.Features: Specifically designed for formability; Retains mechanical properties in the curved condition; Offers cost savings for curved panels.Applications: The HexWeb® Nonmetallic Flex-Core® cell configuration as opposed to the standard hexagonal cell honeycomb provides for exceptional formability into compound curvatures with reduced anticlastic curvature and controlled buckling of cell walls. When formed into tight radii, HexWeb® Nonmetallic Flex-Core® provides higher shear strengths than comparable hexagonal cores of equivalent density. HexWeb® Nonmetallic Flex-Core® applications exist wherever extreme curvature dictates a flexible cell geometry, e.g. radomes, ducts, leading edges of wings and stabilizers.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Hexcel-HexWeb-HRPF50-35-Nonmetallic-Flex-Core-Honeycomb.php

Physical Properties	Metric	English	Comments	
Density	0.0561 g/cc	0.00203 lb/in <sup>3</sup>		
Mechanical Properties	Metric	English	Comments	
Compressive Yield Strength	>= 1.55 MPa	>= 225 psi	Bare, min	
	>= 1.76 MPa	>= 255 psi Stabilized, min		
	2.17 MPa	315 psi	Bare, typ	
	2.72 MPa	395 psi	Stabilized, typ	
Shear Modulus	0.0552 GPa	8.00 ksi	Plate Shear, W Direction, typ	
	0.110 GPa	16.0 ksi	Plate Shear, L Direction, typ	
Shear Strength	>= 0.448 MPa	>= 65.0 psi	Plate Shear, W Direction, min	
	0.621 MPa	90.0 psi	Plate Shear, W Direction, typ	
	>= 0.896 MPa	>= 130 psi	Plate Shear, L Direction, min	
	1.17 MPa	170 psi	Plate Shear, L Direction, typ	

Thermal Properties	Metric	English	Comments	
Maximum Service Temperature, Air	177 °C	350 °F		

## Contact Songhan Plastic Technology Co.,Ltd.



Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China