

## Hexion Bakelite™ PF 84 Phenolic Formaldehyde Resin, Special Preparation Cylindrical Pellets, High Mechanical Strength &

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic

### Material Notes:

Phenolic molding compound, organically filled, reinforced with cotton fibers, increased notched impact strength, standardized molding compound. Application areas: Contact support power switch, moldings for increased mechanical stress, housings, rolls, cog wheels, pulleys, operating elements, covers, roll bodies and bearings. Information provided by Bakelite AG. Bakelite AG became a part of Hexion in 2005.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hexion-Bakelite-PF-84-Phenolic-Formaldehyde-Resin-Special-Preparation-Cylindrical-Pellets-High-Mechanical-Strength-.php](http://www.lookpolymers.com/polymer_Hexion-Bakelite-PF-84-Phenolic-Formaldehyde-Resin-Special-Preparation-Cylindrical-Pellets-High-Mechanical-Strength-.php)

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	ISO 1183
Apparent Bulk Density	0.550 g/cc	0.0199 lb/in <sup>3</sup>	ISO 60
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	Compression molding; ISO 2577

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	250 MPa	36300 psi	H 961/30; ISO 2039/P1
Flexural Strength	95.0 MPa	13800 psi	2 mm/min; ISO 178
Flexural Modulus	7.50 GPa	1090 ksi	ISO 178
Charpy Impact Unnotched	0.800 J/cm <sup>2</sup> @Temperature 23.0 °C	3.81 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179-1/2 eU
Charpy Impact, Notched	0.550 J/cm <sup>2</sup> @Temperature 23.0 °C	2.62 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179-1/2 eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 °C	266 °F	<20000 hours; IEC 60216-P1
	160 °C	320 °F	< 50 hours; IEC 60216-P1
Deflection Temperature at 8.0 MPa	115 °C	239 °F	ISO 75-2
Shrinkage	0.500 % @Temperature 110 °C	0.500 % @Temperature 230 °F	Compression molding; ISO 2577

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	IEC 60093

Electrical Properties	Metric	English	Comments
Surface Resistance	$1.00 \times 10^9$ ohm	$1.00 \times 10^9$ ohm	IEC 60093
Dielectric Constant	15	15	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	15.0 kV/mm	381 kV/in	IEC 60243-P1
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Dissipation Factor	0.30	0.30	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	125 V	125 V	Test liquid A; IEC 60112

Processing Properties	Metric	English	Comments
Feed Temperature	60.0 - 75.0 °C	140 - 167 °F	Injection molding
Nozzle Temperature	80.0 - 100 °C	176 - 212 °F	Injection molding
Melt Temperature	80.0 - 100 °C	176 - 212 °F	Injection molding
Mold Temperature	160 - 190 °C	320 - 374 °F	Injection molding
	160 - 190 °C	320 - 374 °F	Compression molding
Injection Pressure	>= 15.0 MPa	>= 2180 psi	Compression and injection cavity mold pressure
Back Pressure	0.500 - 2.00 MPa	72.5 - 290 psi	Injection molding
Cure Time	0.167 - 0.333 min	0.00278 - 0.00556 hour	Per 1 mm of wall thickness, injection molding
	0.333 - 0.667 min	0.00556 - 0.0111 hour	Per 1 mm of wall thickness, compression molding

Descriptive Properties	Value	Comments
Chromatic Spectrum	Subdued Colors	
Creep Rupture Strength	Good	
Holding Pressure	Approximately 40-60% of injection pressure	
Media Resistance	Good	
Moisture Absorption	90 mg	ISO 62, 24 hours at 23°C
Reserves by Peak Temperature	High	
Thermal Expansion	Slight	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**