

## Hippe PF CC 202 Woven Cotton Cloth Reinforced Phenolic Resin - Sheet

Category : Polymer , Thermoset , Phenolic

**Material Notes:**Used in mechanical and electrical applications (coarse weave: >130 g/m<sup>2</sup>, =30 threads/cm). Information provided by Hippe.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hippe-PF-CC-202-Woven-Cotton-Cloth-Reinforced-Phenolic-Resin-Sheet.php](http://www.lookpolymers.com/polymer_Hippe-PF-CC-202-Woven-Cotton-Cloth-Reinforced-Phenolic-Resin-Sheet.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 - 1.40 g/cc	1.30 - 1.40 g/cc	IEC 1212-2 8.1

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 60.0 MPa	>= 8700 psi	IEC 1212-2 5.7
Flexural Strength	>= 90.0 MPa	>= 13100 psi	Perpendicular to laminations; IEC 1212-2 5.1
Flexural Modulus	>= 7.00 GPa	>= 1020 ksi	IEC 1212-2 5.2
Shear Strength	>= 20.0 MPa	>= 2900 psi	Parallel to laminations; IEC 1212-2 5.6
Izod Impact, Unnotched (ISO)	>= 5.90 kJ/m <sup>2</sup>	>= 2.81 ft-lb/in <sup>2</sup>	Parallel to laminations; IEC 1212-2 5.5.3
Charpy Impact Unnotched	>= 0.780 J/cm <sup>2</sup>	>= 3.71 ft-lb/in <sup>2</sup>	Parallel to laminations; IEC 1212-2 5.5.2

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 5.00e+7 ohm	>= 5.00e+7 ohm	After immersion in water; IEC 1212-2 6.3
Dielectric Constant	<= 5.5 @Frequency 48.0 - 62.0 Hz	<= 5.5 @Frequency 48.0 - 62.0 Hz	IEC 1212-2 6.2
Dielectric Breakdown	>= 20000 V @Temperature 90.0 °C	>= 20000 V @Temperature 194 °F	In oil, parallel to laminations; IEC 1212-2 6.2
Comparative Tracking Index	>= 100 V	>= 100 V	IEC 1212-2 6.4

Descriptive Properties	Value	Comments
Thermal Endurance	120 T.I.	IEC 1212-2 7.1
Water Absorption	< 209 mg	IEC 1212-2 8.2; Test piece 50 x 50 x 10 mm

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**