

Hippe PF CP 206 Cellulose Paper Reinforced Phenolic Resin - Sheet

Category : Polymer , Thermoset , Phenolic , Phenolic, Novolac, Cellulose Filled

Material Notes:

Used in mechanical and electrical applications. Good electrical properties under normal humidity. Also available in hot-punching versions. Information provided by Hippe.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hippe-PF-CP-206-Cellulose-Paper-Reinforced-Phenolic-Resin-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 - 1.40 g/cc	1.30 - 1.40 g/cc	IEC 1212-2 8.1

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 70.0 MPa	>= 10200 psi	IEC 1212-2 5.7
Flexural Strength	>= 80.0 MPa	>= 11600 psi	Perpendicular to laminations; IEC 1212-2 5.1
Flexural Modulus	>= 7.00 GPa	>= 1020 ksi	IEC 1212-2 5.2
Compressive Strength	>= 250 MPa	>= 36300 psi	Perpendicular to laminations; IEC 1212-2 5.3
Shear Strength	>= 20.0 MPa	>= 2900 psi	Parallel to laminations; IEC 1212-2 5.6

Electrical Properties	Metric	English	Comments
Insulation Resistance	>= 1.00e+9 ohm	>= 1.00e+9 ohm	After immersion in water; IEC 1212-2 6.3
Dielectric Constant	<= 6.0 @Frequency 1.00e+6 Hz	<= 6.0 @Frequency 1.00e+6 Hz	IEC 1212-2 6.2
Dielectric Breakdown	>= 25000 V @Temperature 90.0 °C	>= 25000 V @Temperature 194 °F	In oil, parallel to laminations; IEC 1212-2 6.2
Dissipation Factor	<= 0.055 @Frequency 1.00e+6 Hz	<= 0.055 @Frequency 1.00e+6 Hz	IEC 1212-2 6.2
Comparative Tracking Index	>= 100 V	>= 100 V	IEC 1212-2 6.4

Descriptive Properties	Value	Comments
Thermal Endurance	105 T.I.	IEC 1212-2 7.1
Water Absorption	< 149 mg	IEC 1212-2 8.2; Test piece 50 x 50 x 10 mm

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China