

## Hippe PF WV 201 Wood veneer Reinforced Phenolic Resin - Sheet

Category : Polymer , Thermoset , Phenolic

**Material Notes:**

Cross plied. Used in mechanical applications. Good mechanical properties. Information provided by Hippe.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hippe-PF-WV-201-Wood-veneer-Reinforced-Phenolic-Resin-Sheet.php](http://www.lookpolymers.com/polymer_Hippe-PF-WV-201-Wood-veneer-Reinforced-Phenolic-Resin-Sheet.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 - 1.40 g/cc	1.30 - 1.40 g/cc	IEC 1212-2 8.1

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 60.0 MPa	>= 8700 psi	IEC 1212-2 5.7
Flexural Strength	>= 100 MPa	>= 14500 psi	Perpendicular to laminations; IEC 1212-2 5.1
Flexural Modulus	>= 14.0 GPa	>= 2030 ksi	IEC 1212-2 5.2
Compressive Strength	>= 220 MPa	>= 31900 psi	Perpendicular to laminations; IEC 1212-2 5.3
Shear Strength	>= 15.0 MPa	>= 2180 psi	Parallel to laminations; IEC 1212-2 5.6
Izod Impact, Unnotched (ISO)	>= 5.90 kJ/m <sup>2</sup>	>= 2.81 ft-lb/in <sup>2</sup>	Parallel to laminations; IEC 1212-2 5.5.3
Charpy Impact Unnotched	>= 1.00 J/cm <sup>2</sup>	>= 4.76 ft-lb/in <sup>2</sup>	Parallel to laminations; IEC 1212-2 5.5.2

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	>= 100 V	>= 100 V	IEC 1212-2 6.4

Descriptive Properties	Value	Comments
Thermal Endurance	120 T.I.	IEC 1212-2 7.1

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China