

Hogen H50S, 50 Silver/50 Tungsten PM Metal Composite

Category: Metal, Metal Matrix Composite, Nonferrous Metal, Precious Metal, Silver Alloy, Refractory Metal, Tungsten Alloy

Material Notes:

Hogen Duralloy refractory alloys are manufactured by pressing, sintering, and infiltrating tungsten with copper or silver. Silver-Tungsten is used when high oxidation-resistant materials are necessary and superior surface is required. Silver-tungsten is also widely used for tips on contact shoe facings used in high frequency continuous welding processes. Data provided by Hogen Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hogen-H50S-50-Silver50-Tungsten-PM-Metal-Composite.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------|-----------------|----------|
| Density | >= 13.2 g/cc | >= 0.477 lb/in³ | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|--------|---------|----------|
| Hardness, Rockwell B | 70 | 70 | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|--------|---------|----------|
| Silver, Ag | 50 % | 50 % | |
| Tungsten, W | 50 % | 50 % | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China