

## Honeywell ACLAR® 22C (2.00 mil) Copolymer Film (discontinued \*\*)

Category : Polymer , Film , Thermoplastic , Fluoropolymer

### Material Notes:

Description: ACLAR® 22C is a copolymer film consisting primarily of chlorotrifluoroethylene (CTFE). It has moisture barrier and is used for electroluminescent lamps. Information provided by Honeywell.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Honeywell-ACLAR-22C-200-mil-Copolymer-Film-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Honeywell-ACLAR-22C-200-mil-Copolymer-Film-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Specific Gravity	2.09 g/cc	2.09 g/cc	ASTM D1505
Density	2.08 g/cc	0.0750 lb/in <sup>3</sup>	Yield Density
Water Vapor Transmission	0.250 g/m <sup>2</sup> /day	0.0161 g/100 in <sup>2</sup> /day	100°F (37.8°C) / 100%RH; ASTM F1249
Thickness	50.8 microns	2.00 mil	

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	125 - 225 %	125 - 225 %	ASTM D882
Film Elongation at Break, TD	150 - 250 %	150 - 250 %	ASTM D882
Secant Modulus, MD	0.138 - 0.172 GPa	20.0 - 24.9 ksi	ASTM D882
Secant Modulus, TD	0.124 - 0.152 GPa	18.0 - 22.0 ksi	ASTM D882
Tear Strength Test	250 - 325	250 - 325	graves tear TD, grams/mil; ASTM D1004
	325 - 350	325 - 350	graves tear MD, grams/mil; ASTM D1004
Film Tensile Strength at Break, MD	55.2 - 68.9 MPa	8000 - 10000 psi	ASTM D882
Film Tensile Strength at Break, TD	34.5 - 48.3 MPa	5000 - 7000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.230 W/m-K	1.59 BTU-in/hr-ft <sup>2</sup> -°F	
Melting Point	190 °C	374 °F	crystalline melting point; ASTM D4591
Oxygen Index	100 %	100 %	ASTM D2863
Shrinkage, MD	5.0 - 10 %	5.0 - 10 %	300°F / 149°C - 10 min.; ASTM D1204
Shrinkage, TD	-10.0 - -5.00 %	-10.0 - -5.00 %	300°F / 149°C - 10 min.; ASTM D1204

Optical Properties	Metric	English	Comments
Haze	<= 1.0 %	<= 1.0 %	ASTM D1003

Descriptive Properties	Value	Comments
Flammability	non flammable	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China