

Honeywell Aegis™ H135KQP Nylon 6 Extrusion Grade Homopolymer Film (discontinued **)

Category : Polymer , Film , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Extruded

Material Notes:

Description: Aegis H135KQP is a lubricated high viscosity, N6 film extrusion grade homopolymer for cast or blown film. It conforms to applicable FDA requirements, including 21 CFR 177.1500 for N6 and is Kosher approved with certification from Star-K Kosher Certification and Certified Plastic. It possesses the combination of strength, toughness and thermo-forming properties associated with N6 as well as excellent heat, chemical, and abrasion resistance. Applications: Processed Meat Fresh Red Meat Poultry Fish Cheese Dried Food Chilled Fruit Juices Information provided by Honeywell.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Honeywell-Aegis-H135KQP-Nylon-6-Extrusion-Grade-Homopolymer-Film-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D1505
Water Absorption	0.80 %	0.80 %	Extractable Content
	1.6 %	1.6 %	in 24 hours
Moisture Absorption at Equilibrium	2.7 %	2.7 %	at 50% RH
Water Absorption at Saturation	9.5 %	9.5 %	
Oxygen Transmission Rate	40.3 cc/m ² /day	2.60 cc/100 in ² /day	
Nitrogen Transmission	14.0 cc-mm/m ² -24hr-atm	35.6 cc-mil/100 in ² -24hr-atm	cc/m ² /day, No thickness given
Carbon Dioxide Transmission	72.8 cc-mm/m ² -24hr-atm	185 cc-mil/100 in ² -24hr-atm	cc/m ² /day, No thickness given
Viscosity Measurement	135	135	FAV; ASTM D789
Maximum Moisture Content	0.080	0.080	
Melt Flow	1.2 g/10 min @Load 1.00 kg, Temperature 235 °C	1.2 g/10 min @Load 2.20 lb, Temperature 455 °F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ASTM D3418

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	230 - 260 °C	446 - 500 °F	Cast Film

Processing Properties	246 - 254 °C Metric	475 - 489 °F English	Tubular (Blown) Film Comments
Adapter Temperature	260 °C	500 °F	Tubular (Blown) Film
	260 - 266 °C	500 - 511 °F	Cast Film
Die Temperature	254 °C	490 °F	Tubular (Blown) Film
	260 °C	500 °F	Cast Film
Melt Temperature	254 - 260 °C	489 - 500 °F	Tubular (Blown) Film
	260 - 270 °C	500 - 518 °F	Cast Film
Moisture Content	0.080 %	0.080 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China