

Huntsman AVALON[®] 75 AE Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Introduction: AVALON 75 AE is a general purpose polyester based thermoplastic polyurethane for injection molding. AVALON 75 AE is part of the AVALON Soft Range and offers a premium soiling material for casual, sport and protective foot wear. The features offered include: Durability, Excellent surface definition, Abrasion resistance, Slip resistance, Phthalate free TPU. Information provided by Alliance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-AVALON-75-AE-Thermoplastic-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ISO 2781

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	ISO 868
Tensile Strength at Break	24.0 MPa	3480 psi	ISO 37
Elongation at Break	600 %	600 %	ISO 37
100% Modulus	0.00400 GPa	0.580 ksi	ISO 37
300% Modulus	0.00700 GPa	1.02 ksi	ISO 37
Tear Strength	70.0 kN/m	399 pli	ISO 34B
Abrasion	35	35	mm ³ ; ISO 4649
Compression Set	20 %	20 %	ISO 815

Processing Properties	Metric	English	Comments
Feed Temperature	25.0 - 35.0 Â°C	77.0 - 95.0 Â°F	
Rear Barrel Temperature	175 - 185 Â°C	347 - 365 Â°F	
Middle Barrel Temperature	180 - 190 Â°C	356 - 374 Â°F	
Front Barrel Temperature	185 - 195 Â°C	365 - 383 Â°F	
Nozzle Temperature	175 - 190 Â°C	347 - 374 Â°F	
Mold Temperature	25.0 - 50.0 Â°C	77.0 - 122 Â°F	
Injection Pressure	2.00 - 10.0 MPa	290 - 1450 psi	
Hold Pressure	1.00 - 5.00 MPa	145 - 725 psi	

Processing Properties	Metric	English	Comments
Screw Speed	20 - 80 rpm	20 - 80 rpm	

Descriptive Properties	Value	Comments
Compression Ratio	2-3:1	
L/D Ratio	20-25:1	
Ross Flex	-10Å°C, BS 5131	
Typical Screw Diameter	40-120 nm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China