

Huntsman Araldite 98-311 Bisphenol F Epoxy Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 182 to 192. Max color is 2. Comments/Applications: Bisphenol A/F, modified with reactive diluents. Non-crystallizing. Very low viscosity. Used in civil engineering applications, flooring, epoxy mortars, tank linings for metal and concrete, light-colored or clear topcoats. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-98-311-Bisphenol-F-Epoxy-Resin.php

Physical Properties	Metric	English	Comments
Viscosity	1000 - 13000 cP	1000 - 13000 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China