

Huntsman Araldite DY 023 Reactive Diluent

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 167 to 182. Max color is 1. Comments/Applications: Cresyl glycidyl ether - monofunctional epoxy. Less volatile and better resistance to water, but less efficient viscosity reduction than RD-1. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-DY-023-Reactive-Diluent.php

Physical Properties	Metric	English	Comments
Viscosity	5.0 - 25 cP	5.0 - 25 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China