

## Huntsman Araldite EPN 1138 Epoxy Phenol Novolac

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

### Material Notes:

Weight per Epoxide (EEW, g/eq) 176 to 181. Max color is 2. Comments/Applications: Epoxy phenol novolac for higher heat and chemical resistance than PY 307-1 and EPN 1139 or EPN 1179. Used in coatings and composites applications including filament winding, casting and pultrusion. Epoxy functionality of 3.6. Much higher viscosity than EPN 1139. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-Araldite-EPN-1138-Epoxy-Phenol-Novolac.php](http://www.lookpolymers.com/polymer_Huntsman-Araldite-EPN-1138-Epoxy-Phenol-Novolac.php)

Physical Properties	Metric	English	Comments
Viscosity	20000 - 50000 cP	20000 - 50000 cP	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China