

Huntsman Araldite EPN 1139 Epoxy Phenol Novolac

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 172 to 179. Max color is 3. Comments/Applications: Epoxy phenol novolac for use in tank linings, high performance coatings. Used in matrix applications including filament winding, casting and pultrusion. Epoxy functionality of Viscosity between PY 307-1 and EPN 1138 or EPN 1180. High performance, chemically resistant tank linings, maintenance coatings. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-EPN-1139-Epoxy-Phenol-Novolac.php

Physical Properties	Metric	English	Comments
Viscosity	1100 - 1700 cP	1100 - 1700 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China