

Huntsman Araldite GT 7071 US Bisphenol A Epoxy Solid Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 450 to 530. Max color is 2. Comments/Applications: Unmodified bis A "Type 1" epoxy. For use in marine/maintenance coatings, flooring and general purpose. Base resin used in GZ 471 and GZ 571 resin solutions. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-GT-7071-US-Bisphenol-A-Epoxy-Solid-Resin.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	65.0 - 75.0 Â°C	149 - 167 Â°F	Softening Range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China