

Huntsman Araldite GT 7074 Bisphenol A Epoxy Solid Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 935 to 1175. Max color is 2. Comments/Applications: Unmodified bis A "Type 4+" epoxy. Medium melt viscosity epoxy for thick film powder coatings. Outstanding adhesion; excellent impact resistance. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-GT-7074-Bisphenol-A-Epoxy-Solid-Resin.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	97.0 - 110 Â°C	207 - 230 Â°F	Softening Range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China