

## Huntsman Araldite GY 285 Bisphenol F Epoxy Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

### Material Notes:

Weight per Epoxide (EEW, g/eq) 163 to 172. Max color is 5. Comments/Applications: Used in coatings, adhesives, tank linings, flooring, filament winding, casting pultrusion and RTM. Better chemical resistance than GY 6010 especially to organic solvents. Very low viscosity, unmodified bisphenol F epoxy resin. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-Araldite-GY-285-Bisphenol-F-Epoxy-Resin.php](http://www.lookpolymers.com/polymer_Huntsman-Araldite-GY-285-Bisphenol-F-Epoxy-Resin.php)

Physical Properties	Metric	English	Comments
Viscosity	2000 - 3000 cP	2000 - 3000 cP	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China