

Huntsman Araldite GY 6005 Bisphenol A Epoxy Liquid Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 182 to 196. Max color is 1. Comments/Applications: Slightly modified GY 6010. Medium viscosity, general purpose, highly versatile resin for use in cold or heat-cured systems. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-GY-6005-Bisphenol-A-Epoxy-Liquid-Resin.php

Physical Properties	Metric	English	Comments
Viscosity	7500 - 9500 cP	7500 - 9500 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China