

Huntsman Araldite GZ 471 X-75 Bisphenol A Epoxy Solution

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 450 to 530. Max color is 3. Comments/Applications: GT 7071 - 75% solids in xylene. High performance 2-package system for coatings, flooring and general purpose application. Viscosity, Gardner Holdt at 25°C: Z3-Z5. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-GZ-471-X-75-Bisphenol-A-Epoxy-Solution.php

Physical Properties	Metric	English	Comments
Viscosity	4500 - 9000 cP	4500 - 9000 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China