

Huntsman Araldite GZ 540 X-90 Bisphenol A Epoxy Solution

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 233 to 278. Max color is 3. Comments/Applications: GY 6040 - 90% solids in xylene. General purpose bis A epoxy solution for use in 2-package maintenance and architectural coatings. Viscosity, Gardner Holdt at 25°C: Z4-Z6 Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-GZ-540-X-90-Bisphenol-A-Epoxy-Solution.php

Physical Properties	Metric	English	Comments
Viscosity	6000 - 40000 cP	6000 - 40000 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China