

## Huntsman Araldite GZ 571 T-75 Bisphenol A Epoxy Solution

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

### Material Notes:

Weight per Epoxide (EEW, g/eq) 450 to 530. Max color is 5. Comments/Applications: GT 7071 - 75% solids in toluene. High performance 2-package system for coatings, flooring and general purpose applications. Viscosity, Gardner Holdt at 25°C: Z2-Z4. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-Araldite-GZ-571-T-75-Bisphenol-A-Epoxy-Solution.php](http://www.lookpolymers.com/polymer_Huntsman-Araldite-GZ-571-T-75-Bisphenol-A-Epoxy-Solution.php)

Physical Properties	Metric	English	Comments
Viscosity	2500 - 6000 cP	2500 - 6000 cP	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China