

## Huntsman Araldite GZ 597 KT-55 Bisphenol A Epoxy Solution

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

### Material Notes:

Weight per Epoxide (EEW, g/eq) 1666 to 2000. Max color is 4. Comments/Applications: GT 7097 - 55% solids in MIBK (22.5%) and toluene (22.5%). For heat cured industrial coatings in combination with urea, melamine and/or phenolic resins. Viscosity, Gardner Holdt at 25°C: Y-Z2Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-Araldite-GZ-597-KT-55-Bisphenol-A-Epoxy-Solution.php](http://www.lookpolymers.com/polymer_Huntsman-Araldite-GZ-597-KT-55-Bisphenol-A-Epoxy-Solution.php)

Physical Properties	Metric	English	Comments
Viscosity	1800 - 4500 cP	1800 - 4500 cP	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China