

Huntsman Araldite GZ 7071 OX-65 Bisphenol A Epoxy Solution

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 455 to 525. Max color is 2. Comments/Applications: GT 7071 - 65% solids in Aromatic 100 (13%) and xylene (22%) High performance 2-package systems for coatings, flooring and general purpose. Viscosity, Gardner Holdt at 25°C: V-XData provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-GZ-7071-OX-65-Bisphenol-A-Epoxy-Solution.php

Physical Properties	Metric	English	Comments
Viscosity	900 - 1300 cP	900 - 1300 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China