

Huntsman Araldite GZ 7488 V-40 Bisphenol A Epoxy Solution

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 6600 to 10000. Max color is 4. Comments/Applications: Very high molecular weight epoxy resin, 40% solids in PM acetate. Outstanding adhesion, excellent flexibility and toughness for use in heat cured industrial coatings with urea, melamine and phenolic resins. Also zinc rich primers. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-GZ-7488-V-40-Bisphenol-A-Epoxy-Solution.php

Physical Properties	Metric	English	Comments
Viscosity	3000 - 6000 cP	3000 - 6000 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China