

Huntsman Araldite PY 302-2 Bisphenol F Epoxy Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 170 to 177. Max color is 3. Comments/Applications: Bisphenol A/F, non-crystallizing, low viscosity.

Excellent mechanical properties. Used in coatings, adhesives, tank linings, flooring, filament winding, casting and pultrusion. Better chemical resistance especially to organic solvents than GY 6010. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-PY-302-2-Bisphenol-F-Epoxy-Resin.php

Physical Properties	Metric	English	Comments
Viscosity	6500 - 8000 cP	6500 - 8000 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China