

Huntsman Araldite PY 307-1 Epoxy Phenol Novolac

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 170 to 179. Max color is 4. Comments/Applications: Epoxy functionality of 2.4. EPN 1139 or EPN 1179 type with much lower viscosity. FDA listed. For high performance (chemical, solvent and heat resistance) coatings and tank linings. Used in matrix applications; filament winding, casting and pultrusion. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-PY-307-1-Epoxy-Phenol-Novolac.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------|------------------|----------|
| Viscosity | 30000 - 50000 cP | 30000 - 50000 cP | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China